

Brian H3

Technical specifications

Polietileno LDPE Polifen 641 (polietileno resina 641 prime)

PROPIEDADES / CARACTERÍSTICAS	UNITS	METHOD	ESPECIFICACIÓN	
			Minimum	Maximum
Color	N/A	ASTM D 6290	55	
contamination	N/A	DOW OP 01		
Big				1,3
Medium				2,0
Small				2,5
Density to 23°C	g/mL	ASTM D 792	0,9203	0,9243
Mesh granulation 6-8	g/100 g	ASTM D 1921	93	
Gels	N/A	ASTM D 3351		
Big				4
Medium				19
Small				75
fusion index, Mi	g/10 min	ASTM D 1238	1,70	2,30
Slip additive, erucamide	mg/Kg	DOW OP 32	598	808
Anti-blocking additive, silica	mg/Kg	ASTM D 5630	1.069	1.444